

Product Data Sheet

HYTHERM[®] CG (Cellular Glass) INSULATION TORCHED

Non-combustible, high performance flat board or tapered* insulation for warm roof constructions

Hytherm CG Torched is a robust, non-combustible insulation material that can play a crucial role in the fire safety of a building as well as providing long-lasting thermal performance in a torch-applied warm roof waterproofing system.

Hytherm CG Torched is manufactured from specially graded recycled glass (>60%) and natural raw materials such as sand, lime, dolomite. The cellular glass slabs are bonded together with an upper surface coating of a bitumen layer covered with a PE foil to allow direct torching of waterproofing membranes. The lower surface is covered with white glass fleece. The insulation does not combust, support fire, produce fumes or present a fire risk with the building structure and meets the most stringent European fire classification.

The inherent characteristics of this robust material ensure that Hytherm CG Torched insulation provides secure, long-lasting performance without degradation together with design flexibility on the most aesthetically and technically demanding of projects.



Key benefits

Non-combustible to classification EN 13501-1 A1. No propagation of flames in the event of fire (chimney effect) in ventilation space.

High compressive strength due to cell structure. Long-term compressive loads can be applied without movement of deformation.

Waterproof due to hermetically sealed closed cell glass structure. Does not absorb water or swell.

Vapour and gas resistant; provides constant thermal performance for the lifetime of a building.

Dimensionally stable; no warping, creep, swelling or shrinkage.

Resistant to acids and organic solvents; not damaged by aggressive environments.

Rot- and vermin-proof due to being inorganic; no risk of nesting or seed germination.

User-friendly; easy to cut with simple tools and to install.

Ecological; contains recycled glass and can be safely recycled after use.

Environmental credentials:

- Inert and non-toxic
- Manufactured to ISO 14001.
- GWP (Global Warming Potential) = <1.5
- ODP (Ozone Depletion Potential) = zero

Performance

Hytherm CG Torched has a hermetically sealed, closed glass cell structure. It is non-toxic, does not combust or support fire nor does it produce fumes. Its structure also prevents water penetration or tracking by capillary action. If fully bonded (including the board edges) the insulation and its adhesive are vapour tight, fulfilling both insulating and air and vapour control properties in one material. Please contact Axter for more details.

Use

Hytherm CG Torched is designed for use as flat board or tapered insulation in a torch-applied warm roof bitumen waterproofing system on concrete, metal or timber decks.

It can be used as a single or multi-layer insulation system where it is mechanically fixed or bonded using an Axter approved adhesive.

Due to its low coefficient of thermal movement, Hytherm CG is simply bonded onto the deck with adhesive, avoiding thermal bridging and corrosion of mechanical fixings. It is ideal as part of waterproofing design for heavy traffic roofs due to it having one of the highest compressive strengths, including at edges, of any insulating material.

Adhesives

The following Axter adhesives are recommended for use with Hytherm CG Torched insulation:

Hyrastik Evo - non-flammable, solvent-free, polyurethane cold applied adhesive

Hyrastik Evo is a high performance, single-component, moisture-curing polyurethane insulation adhesive developed to provide a safe, flame free and effective solution to bonding insulation securely to roof decks.

Supplied in a 6 litre tin which includes a spout for simple pouring.

| | | | |
|--------------------------------|------------------------|----------------------------|-----------------------------------|
| Product | Hyrastik (100% solids) | Open Time (10°C) | 15 minutes |
| Appearance | Brown | Open Time (20°C) | 7 minutes |
| Application Temperature | 5 - 30°C | Open Time (30°C) | 4 minutes |
| Temperature Resistance | -30 - 100°C | Coverage | 30-60 m ² / 6l (6.5kg) |
| Cure Time (10°C) | 60 minutes | Viscosity (CPS) | 4,000 |
| Cure Time (20°C) | 30 minutes | Storage temperature | 5 - 30°C |
| Cure Time (30°C) | 15 minutes | Environmental | Solvent-free Non-flammable |

Full details are given in the Axter Hyrastik Evo Product Data Sheet and Safety Data Sheet.

Starcoat R - cold applied bitumen adhesive

Starcoat R is a single-component, polyurethane bitumen adhesive for insulation, with integrated anti-root protection. It is a flame free, cold applied product and is ready to use with no mixing.

Starcoat R is also ideal for the waterproofing of complex details and localised repairs on new and existing bitumen membranes on inaccessible areas, areas with pedestrian and light vehicular traffic and on living roofs. Eliminating the need for naked flame gas torches, it is the ideal choice for high risk detail and perimeter zones.

Application of Starcoat R in a continuous coat, sealing all board edges, will negate the need for an air and vapour control layer (AVCL).

Supplied in 4 x 4kg or in 20 kg drum. Application is by brush or roller.

| | | | |
|--------------------------------|------------|---|--|
| Product | Starcoat R | Coverage rate ** | 1.5kg / m ² |
| Appearance | Black | Coverage rate/unit/m² ** 4x4kg drum 20kg drum | 10.67 m ² 13.33 m ² |
| Application Temperature | 5 to 35°C | Drying time hour/layer* | 3 to 24 |

*drying time will vary, figures assume 25°C and 50% humidity.

**coverage rates will vary depending on porosity and condition of substrate.

Full details are given in the Axter Starcoat R Brochure, Technical Data Sheet and Safety Data Sheet.

Ruberfix Bitumen Mastic - hot applied adhesive

Ruberfix is a bitumen mastic (no oxidised bitumen content) for use with Hytherm CG insulation, bitumen waterproofing membranes and also to fill joints and bridge cracks. Application of Ruberfix bitumen mastic in a continuous coat, sealing all board edges, will negate the need for an air and vapour control layer (AVCL). The bitumen blocks are heated with the plastic film intact in a thermostatically-controlled bitumen boiler with regulator and the mastic is applied from a pouring can with a large aperture prior to installation of the insulation.

Supplied in 20kg blocks wrapped in thermofusible film.

| | | | |
|-------------------|-------------------------|---|----------------------------|
| Product | Ruberfix bitumen mastic | Melting Temperature | 150 °C to 170°C |
| Appearance | Black | Coverage rate: Hytherm CG insulation | 5kg / m ² |
| | | Bitumen waterproofing membranes | 2.5 to 3/kg/m ² |

Full details are given in the Axter Ruberfix bitumen mastic Technical Data Sheet and Safety Data Sheet.

Green Roofs

Hytherm CG Torched can be incorporated into an extensive or intensive living roof. Depending on structural conditions it is suitable for concrete, timber or metal decks. It is resistant to the increased amount of vapour and moisture on roofs with planted areas and because it is inorganic, it is highly resistant to all forms of infestation and vermin. The closed glass cells do not store moisture and provide an effective shield against root penetration. There is no risk of fertilizer damaging the insulation as it is resistant to chemicals.

Environment and Ecology

Hytherm CG Torched is manufactured from minimum specially graded recycled glass (>60%), including scrap vehicle glass and off-cuts from the glazing sector, and natural raw materials (sand, dolomite, lime). It is an inert and non-toxic material and at the end of a building's life the Hytherm CG Torched insulation can be safely incorporated into hardcore or landscaping.

The glass cell structure of the material is naturally produced and is inorganic and free from ozone-depleting propellants, flame retardants or binders. It is without VOC or other volatile substances. Mutagenic or carcinogenic chemicals are not used during production.

HYTHERM CG TORCHED – Standard Thicknesses & Characteristics

| Length x width (mm) | 1200 x 600 | | | | | | | |
|--|------------|------|------|------|------|------|------|------|
| Thickness (mm) | 50 | 60 | 70 | 80 | 90 | 100 | 110 | 120 |
| (R _D) - m ² K/W | 1.35 | 1.65 | 1.90 | 2.20 | 2.50 | 2.75 | 3.05 | 3.30 |
| Units | 5 | 4 | 4 | 3 | 3 | 3 | 2 | 2 |
| m ² | 3.60 | 2.88 | 2.88 | 2.16 | 2.16 | 2.16 | 1.44 | 1.44 |

| Length x width (mm) | 1200 x 600 | | | | | | | |
|--|------------|------|------|------|-------|-------|--|---|
| Thickness (mm) | 130 | 140 | 150 | 160 | 170 | 180 | | |
| (R _D) - m ² K/W | 3.60 | 3.85 | 4.15 | 4.40 | 4.70 | 5.00 | | |
| Units | 2 | 2 | 2 | 2 | 14* | 14* | | 2 |
| m ² | 1.44 | 1.44 | 1.44 | 4.44 | 10.08 | 10.08 | | |

Other dimensions and thicknesses are available on request

*No single package but 14 boards on a pallet

HYTHERM CG TORCHED – Product Characteristics

| Product characteristics to EN 13167 | Measure unit | Value | Standard |
|-------------------------------------|-------------------|--|----------------|
| Reaction to fire | | Euroclass E Core material complies with Euroclass A1, non combustible, no toxic fumes | EN 13501-1 |
| Density (±15%) | kg/m ³ | 100 | EN 1602 |
| Thickness ± 2mm | mm | from 50 to 180mm | EN 823 |
| Length ± 5mm | mm | 1200 | EN 822 |
| Width ± 2 mm | mm | 600 | EN 822 |
| Thermal Conductivity | W/mK | $\lambda_D \leq 0.036$ | EN ISO 10456 |
| Point load | mm | $PL \leq 1.5$ | EN 12430 |
| Compressive strength | kPa | $CS \geq 500$ | EN 826 Annex A |
| Bending strength | kPa | $BS \geq 450$ | EN 12089 |
| Tensile strength | kPa | $TR \geq 100$ | EN1607 |

HYTHERM CG TORCHED – Product Characteristics

| Product characteristics to EN 13167 | Measure unit | Value | Standard |
|-------------------------------------|-----------------|--------------------|---------------|
| Service temperature limits | °C | -265 to +430 | |
| Water vapour resistance | μ | ∞ | EN ISO 10456 |
| Hygroscopicity | | zero | |
| Capillarity | | zero | |
| Melting point | °C | >1000 | cf DIN 4102-7 |
| Thermal expansion coefficient | K ⁻¹ | 9×10^{-6} | EN 13471 |
| Specific Heat | J/(kg.K) | 1000 | EN ISO 10456 |

Environmental Product Declaration: EPD-PCE-20150042-IBA1-DE (ISO 14025 and EN 15804)

Technical Guidelines

Application

Application of Hytherm CG Torched should preferably take place when the ambient air temperature and temperature of the deck/roof slab are above 5°C.

All expansion and movement joints should be continued through the structure.

Decks

Metal

| | |
|------------------------------|--|
| Thickness | Minimum 0.7mm |
| Trough width | Maximum 60% of total surface |
| Minimum insulation thickness | in function of the trough width (L1) $0\text{mm} < L1 \leq 80\text{mm} = \text{thickness } 50\text{mm}$ (minimum) $80\text{mm} < L1 \leq 110\text{mm} = \text{thickness } 60\text{mm}$ $110\text{mm} < L1 \leq 140\text{mm} = \text{thickness } 70\text{mm}$ $140\text{mm} < L1 \leq 180\text{mm} = \text{thickness } 80\text{mm}$ |
| Maximum deflection | 1/240 of the span if the height of the corrugations is less than 90mm 1/300 of the span if the height of the corrugations is equal to or more than 90mm |

Metal sheets to be fastened following manufacturer's guidelines.

On top of the galvanized metal sheet a spirit-based primer (cutback) coating should be applied (consumption +/- 150gm/m²). On pre-coated sheets it is not necessary to apply a primer.

Continuous supports

The deck must be clean, dry and free of any irregularities. Irregularities of the deck must not exceed 3mm over 600mm or 5mm over 2m.

In the case of a concrete roof slab and if required an appropriate levelling screed shall be applied.

If composed of pre-cast concrete beams, irregularities must not exceed 3mm between each section.

*Information on HYTHERM CG Adhered and Tapered insulation is available in separate Axter Product Data Sheets. Please contact Axter for further details or technical assistance.

The manufacturer reserves the right without prior notice to modify the composition of these products. Characteristics provided in this publication derive from data obtained under controlled test conditions. Axter Ltd makes no warranties, express or implied, as to the properties and performance under any variations from such conditions in actual construction and accepts no liability for use of these products that does not comply with Axter Ltd specifications.