

Technical Data Sheet

ROLLSTICK 21 Air & Vapour Control Layer (AVCL) Base & Underlayer

Description	ROLLSTICK 21 is a glass-fibre reinforced SBS elastomeric bitumen waterproofing membrane, with semi-continuous strips of self-adhesive bitumen on the surface, protected by a thermofusible film, and a thermofusible film on the undersurface.
Use	<p>An air and vapour control layer (AVCL) low permeability membrane used as part of a system to control the movement of air, water vapour and heat leakage from within the building. Can also be used as base or underlayer as part of a multi-layer waterproofing system and as an adhesive layer + AVCL for insulation.</p> <p>The choice of AVCL will depend on the degree of air and vapour pressure produced, the specified roof deck/slab and the need for a robust temporary waterproofing layer. ROLLSTICK 21 is suitable for use in bitumen and single ply warm roof waterproofing systems.</p>
Application method	Installed fully bonded, with fully sealed joints, using torch-on techniques to form a continuous layer.
Storage	Rolls to be stored upright and away from heat.
Composition	(indicative). See below.

Reinforcement (g/m²) :	Glass-fibre	50
Binder (g/m²) :	SBS elastomer	3,100
Surface finish (g/m²) :	Thermofusible film & adhesive strips	10
Under surface finish (g/m²) :	Thermofusible film	10

Characteristics		Standards (BS)	Units	Value	Tolerance		
					Min	Max	
Dimensions	Length	EN 1848-1	m	7	-1%		
	Width		m	1	-1%		
	Straightness		-	Pass			
	Nominal roll weight		kg	23.1			
	Thickness (finished product)	EN 1849-1	mm	2.20	2.00	2.40	
Visible defects	New product	EN 1850-1	-	None			
	After ageing to EN 1297		-	NA			
Adhesion of granules		EN 12039	%	NA	-	-	
Resistance to tearing (nail shank)	Longitudinal	EN 12310-1	N	80	50	150	
	Cross direction			80	50	150	
Tensile properties: maximum tensile force	Longitudinal	EN 12311-1	N/50 mm	250	200	550	
	Cross direction			150	120	350	
Tensile properties: elongation	Longitudinal	EN 12311-1	%	3	2	-	
	Cross direction			3	2	-	
Peel resistance of joint	Maximum force	EN 12316-1	N/50mm	Selvedge	NA	-	-
				End joint	NA	-	-
	Average force			Selvedge	NA	-	-
				End joint	NA	-	-
Shear resistance of joint	Maximum force	EN 12317-1	N/50mm	Selvedge	NA	-	-
				End joint	NA	-	-
Flexibility at low temperature	Surface	EN 1109	°C	-16	≤		
	Under surface			-16	≤		

Characteristics		Standards (BS)	Units	Value	Tolerance	
					Min	Max
Flow resistance at elevated temperature	New product	EN 1110	°C	100	≥	
	After ageing to EN 1296			NA		
Resistance to impact		EN 12691	mm	500	≤	
Resistance to static loading		EN 12730	kg	NA	≥	
Dimensional stability		EN 1107-1	%	0.1	≤	
Form stability under cyclic temperature change		EN 1108	%	NA		
Water vapour transmission properties	New product	EN 1931	Sd(m)	1000	≥	
	After ageing to EN 1296		Sd(m)	1100	≥	
Watertightness	New product	EN 1928	-	Pass	< 2 kPa	
	After ageing to EN 1296		-	NA		
Watertightness after stretching at low temperature		EN 13897	%	NA		
Reaction to fire		EN 13501-1	-	PND		
Resistance to root penetration		EN 13948	-	NA		
Dangerous substances consult: http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm		-	-	None		

NA=not applicable due to use of product. PND=Performance not determined.

The manufacturer reserves the right to modify, at any time, the characteristics of this product.