



## CARINA PRODUCT SPECIFICATION

| PRODUCT INFORMATION       | PRODUCT SPECIFICATION                                    |                         |
|---------------------------|--|-------------------------|
| Construction              | PVC  |                         |
| Thickness                 | 2,5mm  | EN ISO 24346            |
| Wear Layer                | 0,55mm   | EN ISO 24346            |
| Wear Layer Treatment      | Superguard®  |                         |
| Total Weight              | 4105,5g/m <sup>2</sup>                                   | EN ISO 23997            |
| Plank Size                | 19,6 x 132,0cm   | EN ISO 24342            |
| Planks per box            | 14 pcs/box   | 3,62m <sup>2</sup> /box |
| Tile size                 | 32,9 x 65,9cm  | EN ISO 24342            |
| Box Tiles                 | 16pcs/box  | 3.47m <sup>2</sup> /box |
| Tog Rating                | 0.1  |                         |
| Suitability               | Class 23- Heavy Domestic<br>Class 33-Heavy Commercial    | EN ISO 10874            |
| Imflammability            | Bfl-S1   | EN 13501                |
| Abrasion group            | Class T  | EN ISO 660-2            |
| Scratch Resistance        | ≤MSR-A2, ≤ MSR-B2  | EN ISO 16094            |
| Squareness & Straightness | ≤0,35mm  | EN ISO 24342b           |
| Slip Resistance           | DS   | EN 13893                |
| Slip Restraint            | R10  | DIN 51130               |
| Residual Indentation      | Norm ≤0,10mm<br>Average result measured: 0,03mm          | EN ISO 24343-1          |
| Furniture Leg Resistance  | No Cracks, No Damage                                     | EN ISO 16581            |
| Curling                   | Norm:≤1 2 l mm. Result:≤2mm                              | EN ISO 23999            |
| Electrical Resistance     | ≤10° Ohm   | EN 1081                 |
| Dimensional stability     | Norm: ≤ 1 0,25 l %<br>Average result measured: ≤10,05l % | EN ISO 23999            |
| Heat Insulation           | 0,25 w/(m.K)   | EN ISO 10456            |
| Thermal Resistance        | 0,0100 m <sup>2</sup> . K/W                              | EN 12667                |
| Electrostatic Performance | < 2 kV   | EN 1815                 |
| Formaldehyde Group        | E1   | EN 717-1                |
| Acoustic Insulation       | 4 dB   | EN ISO 717-2            |
| Castor Chair Resistance   | No damage to wear layer, no delamination                 | EN ISO 4918             |
| Stain Resistance          | Very Good  | EN ISO 26987            |
| Light Fastness            | ≥6   | EN ISO 105-B02          |
| Underfloor Heating        | Suitable, max 27°C                                       | EN 12524                |
| Warranty                  | 20 Year Residential<br>10 Year Commercial                |                         |





Furlong Flooring®

First choice flooring for every room

## CARINA PRODUCT SPECIFICATION

### COLOURS

|                        |
|------------------------|
| Alpine Oak 24823       |
| Clearmont Oak 24123    |
| Burlington Oak 24937   |
| Edgerton Oak 24220     |
| Kaycee Oak 24876       |
| Parkerton Oak 22230    |
| Saratoga Oak 22949     |
| Dixon Stone 46905      |
| Glenrock Stone 46953   |
| Jackson Oak 24126      |
| Hartville Oak 24913    |
| Wheatland Oak 24820    |
| Yoder Oak 24867        |
| Marbleton Stone 46156  |
| Rock River Stone 46913 |



|           |   |                           |
|-----------|---|---------------------------|
| <b>CE</b> | <b>EN 14041</b>   | <b>DIVINO</b>             |
|           | 13<br>DOP - LVT<br>IVC bvba<br>Nijverheidslaan 29<br>B - 8580 Avelgem<br>resilient floor covering<br>EN ISO 10982 | <b>Br-s1</b><br><b>DS</b> |



**DARTFORD**  
01322 628700  
**PRESTON**  
01772 316155

**STONEHOUSE**  
01452 228480  
**DUBLIN**  
+353-1-4092000



Alternatively, visit [furlongflooring.com](http://furlongflooring.com)  
or email [enquiries@furlongflooring.com](mailto:enquiries@furlongflooring.com)

Follow us on

