

DECLARATION OF PERFORMANCE
SMARTPLY SURE STEP
Reference Number: UKCADOP11 REV0

SMARTPLY Europe DAC,
Belview, Slieverue,
Waterford,
Ireland.

Product Type	Intended Use	AVCP*	UK Assessment Body
OSB/3	Internal use as structural components in humid conditions	2+	0836
*Assessment and verification of constancy of performance system according to Annex V of regulation (EU) No 305/2011			

Declared Performance

Essential Characteristics	Performance										Designated Standard
	>6 to 10		>10 to 18		>18 to 25		>25 to 32		>32 to 40		
Thickness Range (mm)	0	90	0	90	0	90	0	90	0	90	BS EN 13986:2004 +A1:2015
Angle to Major Axis											
Characteristic Strength (N/mm ²)											
- Bending f_m	NPD	NPD	16.4	8.2	14.8	7.4	NPD	NPD	NPD	NPD	
- Compression f_c	NPD	NPD	15.4	12.7	14.8	12.4	NPD	NPD	NPD	NPD	
- Tension f_t	NPD	NPD	9.4	7.0	9.0	6.8	NPD	NPD	NPD	NPD	
- Panel Shear f_v	NPD		6.8		6.8		NPD		NPD		
- Planar shear f_r	NPD		1.0		1.0		NPD		NPD		
Mean Stiffness (MOE) (N/mm ²)											
- Tension E_t	NPD	NPD	3800	3000	3800	3000	NPD	NPD	NPD	NPD	
- Compression E_c	NPD	NPD	3800	3000	3800	3000	NPD	NPD	NPD	NPD	
- Bending E_m	NPD	NPD	4930	1980	4930	1980	NPD	NPD	NPD	NPD	
- Panel Shear G_v	NPD		1080		1080		NPD		NPD		
- Planar Shear G_r	NPD		50		50		NPD		NPD		
Reaction to Fire (excluding floorings)	NPD		NPD		NPD		NPD		NPD		
Reaction to Fire (floorings)	NPD		NPD		NPD		NPD		NPD		
Water Vapour Permeability μ	NPD		NPD		NPD		NPD		NPD		
- Wet Cup	NPD		NPD		NPD		NPD		NPD		
- Dry Cup	NPD		NPD		NPD		NPD		NPD		
Release of Formaldehyde	E1		E1		E1		E1		E1		
Release (content) of Pentachlorophenol (PCP)	NPD		NPD		NPD		NPD		NPD		
Airborne Sound Insulation (surface mass) (R)	NPD		NPD		NPD		NPD		NPD		
Sound Absorption α (250 – 500 Hz)	0.10		0.10		0.10		0.10		0.10		
Sound Absorption α (1000 – 2000 Hz)	0.25		0.25		0.25		0.25		0.25		
Thermal Conductivity λ	0.11		0.11		0.11		0.11		0.11		

Essential Characteristics	Performance						Designated Standard
Durability							BS EN 13986:2004 +A1:2015
Thickness Range (mm)	6 to 10	>10 to <18	18 to 25	>25 to 32	>32 to 40		
Internal Bond (N/mm²)	NPD	0.32	0.30	NPD	NPD		
Swelling in Thickness (%)	NPD	15	15	NPD	NPD		
Moisture Resistance - Internal Bond after Boil Test (N/mm²)	NPD	NPD	NPD	NPD	NPD		
Moisture Resistance - Internal Bond after Cyclic Test (N/mm²)	NPD	NPD	NPD	NPD	NPD		
Bending Strength after Cyclic Test – Major Axis (N/mm²)	NPD	8	7	NPD	NPD		
Mechanical (creep k_{def}) Service Class 1	NPD	1.50	1.50	NPD	NPD		
Mechanical (creep k_{def}) Service Class 2	NPD	2.25	2.25	NPD	NPD		
Thickness Range (mm)	>6 to 40						
Load-Duration Class	Permanent Action	Long Term Action	Medium Term Action	Short Term Action	Instantaneous Action		
Mechanical (duration of load k_{mod}) Service Class 1	0.40	0.50	0.7	0.90	1.10		
Mechanical (duration of load k_{mod}) Service Class 2	0.30	0.40	0.55	0.70	0.90		
Biological	Use classes 1 & 2						
¹T&G Products	Spacing	12.5mm T&G	15mm T&G	18mm T&G	22mm T&G	24mm T&G	
²Characteristic Point load $F_{max,k}$ (N) (for floors and roofs)	400mm	3019	4815	5494	6709	7610	
	600mm	2766	3807	4712	6575	7272	
Point Load Mean Stiffness (N/mm) (for floors and roofs)	400mm	395	563	797	1161	1305	
	600mm	188	322	426	669	754	
²Characteristic Point Load Serviceability $F_{ser,k}$ (N) (for floors and roofs)	400mm	2113	3370	3846	4696	5327	
	600mm	1936	2665	3298	4603	5091	
Soft Body Impact Resistance Floor/roofs	400mm	Class I	Class I	Class I	Class I	Class I	
	600mm	Class II	Class I	Class I	Class I	Class I	
Soft Body Impact Resistance Walls	Spacing			> 9mm			
	400mm			Class III			
	600mm			Class III			
¹ NPD for square edge products							
² Characteristic means lower 5 th percentile calculated according to EN 1058							

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 as it has effect in the United Kingdom, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Guillaume Coste. Structural Engineer. Waterford, Ireland 24th January 2022.